



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter Media

Ultra-Web® on Spunbond Antistatic

Ultra-Web® on Spunbond Antistatic

Appearance	White, uncorrugated
Use	Pleatable filter media
Composition	Spunbond polyester with nanofiber layer aluminised
Area weight (DIN 53884)	260 g/m ²
Thickness (DIN 53885)	0.61 mm
Air permeability (DIN 53887)	420 m ³ /m ² .h @ 200 Pa
Dimensional stability	N/A
Surface finish	Aluminised
Additional treatments	N/A
Surface electrical resistance (DIN 54345)	Less than 10 ⁴ ohms
BIA Category (DIN 60335-2-69)	
Temperature (dry heat) Continuous Peaks	93°C 110°C
Chemical resistance Hydrolysis Acids Alkalis Oxidising agents Organic solvents	N/A Good Good Good Good
Abrasion resistance	Excellent
Supports Combustion	Yes
Application field	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food and industrial processing, when product contamination must be minimised. Excellent performance on moist, hygroscopic or agglomerative dust. High filtration efficiency on very fine particulate < 1 micron.
Application field example	Chemical processing, food processing, general industrial.

Humberstone Lane
Thurmaston
Leicester LE4 8HP
England
Tel +44 (0)116 269 6161
Fax +44 (0)116 269 3028
Email: IAF-uk@donaldson.com

Research Park Building No. 1303
Interleuvenlaan 1
B-3001 Leuven (Heverlee)
Belgium
Tel +32 (0)16 383 970
Fax +32 (0)16 383 938
Email: IAF-europe@donaldson.com

Publication 421-8062-GB • Rev. 02 • 0511

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.

www.donaldson.com