



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Blended 80/20

Blended 80/20

Appearance	White
Use	Pleatable filter media
Composition	80% Cellulose + 20% Polyester
Area weight (g/m²)	135
Thickness (mm)	0.45
Air Permeability (m³/m²/h - 200 PA)	600
Surface electrical resistance (DIN 54345)	-
IFA/BIA certificate (DIN EN 60335-2-69:2008)	M
Max. working temperature (C°)	80
Volume of pores (%)	71
Application field	Fine dust, fumes from laser and plasma cutting, welding fumes and air suction in gas turbines.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM06584A • Rev. 10 • 0319

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.