



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Polyester + PTFE Coating

Polyester + PTFE Coating

| | |
|---|---|
| Treatment | PTFE Coating |
| Use | Pleatable filter media |
| Composition | 100% Polyester |
| Area weight | 245 g/m ² |
| Thickness | 0.55 mm |
| Air Permeability | 550 m ³ /m ² /h at 200 Pa |
| Surface electrical resistance (Ohm) | - |
| IFA/BIA certificate (DIN EN 60335-2-69:2015) | M |
| Temperature (dry heat) | |
| Continuous | 120 °C |
| Peaks | 140 °C |
| Chemical resistance | |
| Oil/Water | Very Good |
| Hydrolysis | Good |
| Acid | Good |
| Alkali | Fair |
| Dust release | Excellent |

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM06599N • Rev. 01 • 0319

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.