



## DATA SHEET

### Filter media Standard Polyester

#### Standard Polyester

<b>Appearance</b>	White, uncorrugated
<b>Use</b>	Pleatable filter media
<b>Composition</b>	Spunbond polyester
<b>Area weight</b>	250 g/m <sup>2</sup>
<b>Thickness</b>	0.57 mm
<b>Air Permeability</b> (DIN 29073)	470 m <sup>3</sup> /m <sup>2</sup> .h at 200 Pa
<b>IFA/BIA certificate</b> (DIN 660335-2-69)	N/A
<b>Temperature (dry heat)</b>	
Continuous	93 °C
Peaks	110 °C
<b>Chemical resistance</b>	
Hydrolysis	N/A
Acids	Good
Alkalis	Good
Oxidising agents	Good
Organic solvents	Good
<b>Abrasion resistance</b>	Excellent
<b>Supports combustion</b>	Yes
<b>Application field</b>	Wide pleat spacing provides excellent particle release. Highly recommended for chemical, food, and industrial processing when product contamination must be minimised. Excellent performance on moist, hygroscopic or agglomerative dust.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM0506401 • Rev. 11 • 1118

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.