



## DATA SHEET

### Filter media

Polyester

### Polyester

<b>Composition</b>	100% Polyester Spun Bonded media
<b>Area weight</b> (DIN 53884)	265 g/m <sup>2</sup>
<b>Thickness</b> (DIN 53885)	0.7 mm
<b>Air Permeability</b> (DIN 53887)	465 m <sup>3</sup> /m <sup>2</sup> /h at 200 Pa
<b>Surface finish</b>	N/A
<b>Additional treatments</b>	N/A
<b>Surface electrical resistance</b> (DIN 54345)	N/A
<b>IFA/BIA certificate</b> (DIN 660335-2-69)	M
<b>Temperature (dry heat)</b>	
Continuous	130 °C
<b>Dust release properties</b>	Very good
<b>Application field</b>	Most industrial processes, applications in the chemical industry. Shot blasting and powder paint applications as well as other applications in the metal industry.  The media is suitable for coarse and fine dust.

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM083630F • Rev. 00 • 1119

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.