



Donaldson
FILTRATION SOLUTIONS

DATA SHEET

Filter media

Sintered Polyethylene AntiStatic

Sintered Polyethylene AntiStatic

| | |
|------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Appearance | Black |
| Use | Sintamatic sintered panels antistatic |
| Composition | Sintered polyethylene composite material |
| Area weight | Typically 2.6 to 2.9 kg/m ² |
| Thickness | 4 mm |
| Air Permeability (DIN 53887) | 0.95 m ³ /m ² /min@200Pa |
| Dimensional stability at 60°C (%) | < 1.0 |
| Surface finish | PTFE emulsion coating |
| Additional treatments | Antistatic carbon emulsion coating |
| Surface electrical resistance (BGR 132) | Less than 10 ⁸ Ω |
| IFA/BIA category (DIN 660335-2-69) | Class M |
| Temperature (dry heat) | |
| Continuous | 70 °C |
| Peaks | 70 °C |
| Chemical resistance | |
| Hydrolysis | Excellent |
| Acids | Very good |
| Oxidising agents | Good |
| Abrasion resistance | Excellent |
| Supports combustion | Yes |
| What to avoid | Can be degraded by strong oxidising agents such as nitric acid, bromine or chlorine etc. Some organic solvents such as toluene may cause swelling. Avoid very cohesive, sticky materials or moisture sensitive dusts which are likely to crust on the media surface. Also avoid those materials containing oils, fats and greases, etc. |
| Suitable applications | Sintered elements are suitable for the vast majority of chemical conditions likely to be encountered in Sintamatic applications. Any dust handled should be dry and free flowing, free from any oils, fats or greases etc. The antistatic coating prevents the build up of any dangerous static charges inside the filter case. Also, with certain dusts, these charges can have an effect on the dust release properties of the element, thereby influencing the unit performance. |

Order online

shop.Donaldson.com

Contact us

Donaldson.com

Publication DOCAM0833601 • Rev. 00 • 1118

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.