



DATA SHEET

Filter media

Standard Cellulose Flame Retardant with Nanofibres

Standard Cellulose Flame Retardant with Nanofibres

Appearance	Light green, corrugated
Use	Pleatable filter media
Composition	Cellulose fiber filter media with flame retardant treatment and nanofibre layer
Area weight	114 g/m ²
Thickness	0.31 mm
Air Permeability (Frazier)	293 m ³ /m ² .h at 125 Pa
Temperature (dry heat)	
Continuous	65 °C
Peaks	80 °C
Chemical resistance	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising agents	Poor
Organic solvents	Fair
Abrasion resistance	Good
Supports combustion	No. Flame Retardant class F1
Application field	Enhanced performance due to a unique combination of fiber sizes and a more uniform fiber distribution. Suited for applications with dry, coarse particulate. Cellulux media is superior to felts, fabrics, cotton cloths, etc. Typical applications include metal working, shot blasting, etc.

Order online 
shop.Donaldson.com

Contact us
Donaldson.com

Publication DOCAM0838801 • Rev. 00 • 1020

Donaldson reserves the right to change or discontinue any model or specification at any time and without notice. Freedom from patent restrictions must not be assumed.